



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b>  <b>C08J 9/14, 9/12</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/31170</b>  <b>(43) International Publication Date:</b> 24 June 1999 (24.06.99)
<b>(21) International Application Number:</b> PCT/US98/26322  <b>(22) International Filing Date:</b> 11 December 1998 (11.12.98)  <b>(30) Priority Data:</b> 60/069,983 18 December 1997 (18.12.97) US  <b>(71) Applicant (for all designated States except US):</b> THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Mid- land, MI 48674 (US).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> CHAUDHARY, Bharat, I. [IN/US]; 3419 Woodbine Place, Pearland, TX 77584 (US). SUH, Kyung, W. [US/US]; 6204 Evergreen Court, Midland, MI 48642 (US). PAQUET, Andrew, N. [US/US]; 3542 Midland Road, Saginaw, MI 48603 (US).  <b>(74) Agent:</b> ROBERTS, John, H.; Patent Dept., P.O. Box 1967, Midland, MI 48641-1967 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
<b>(54) Title:</b> FOAMS COMPRISING HFC-134 AND A LOW SOLUBILITY CO-BLOWING AGENT AND A PROCESS FOR MAKING		
<b>(57) Abstract</b>  <p>Disclosed is an extruded, dimensionally stable, closed cell alkenyl aromatic polymer foam. The foam comprises an alkenyl aromatic polymer material greater than 50 percent by weight of alkenyl aromatic monomeric units. The foam has a density of about 16 to about 64 kilograms per cubic meter. The foam has a thickness in cross section of 15 millimeters or more. The foam has a blowing agent composition comprising a primary blowing agent of about 70 to about 95 weight percent 1,1,2,2-tetrafluoroethane and a secondary blowing agent comprising about 30 to about 5 weight percent based upon the total moles of the blowing agent composition. The secondary blowing agent being selected from the group consisting essentially of 1,1,1,2-tetrafluoroethane, carbon dioxide, nitrogen, argon, and water. Further disclosed is a process for making the foam.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

# FOAMS COMPRISING HFC-134 AND A LOW SOLUBILITY CO-BLOWING AGENT AND A PROCESS FOR MAKING

## 5 Background of the Invention

The invention relates to extruded alkenyl aromatic polymer foams comprising a blend of 1,1,2,2-tetrafluoroethane (HFC 134) and a low solubility co-blowing agent and a process for making.

10 Due to increasingly stringent environmental regulations, manufacturers of alkenyl aromatic polymer insulating foams are considering fluorocarbons as potential insulating cell gas agents (blowing agents). One such agent is HFC 134.

HFC 134 is known in the art as a blowing agent for making alkenyl aromatic polymer foams. HFC 134 is disclosed in Canadian Patent 1,086,450; Japanese Published Application 5-287111; and U.S. Patent Nos. 5,278,196 and 5,182,040.

15 When selecting a blowing agent for insulating alkenyl aromatic polymer foams, the amount of insulating blowing agent must be high enough to provide adequate insulating performance but not high enough to result in undesirable physical properties in the foam product.

20 A problem with using HFC 134 as a blowing agent is that at levels required to maintain desirable foam insulating performance (i.e. about 70 weight percent or more based upon the total moles of blowing agent), poor dimensional stability is observed when producing closed cell alkenyl aromatic polymer foams of low density (i.e. about 16 to about 64 kilograms per cubic meter) and thick cross-section (i.e. about 15 millimeters or more).

25 The prior art does not effectively address the dimensional stability problem associated with use of high levels of HFC 134 in blowing agents when making closed cell alkenyl aromatic polymer foams of low density and thick cross-section.

30 Canadian Patent No. 1,086,450 relates extruded alkenyl aromatic polymer foams made with 30 to 70 weight percent of a low permeability blowing agent such as HFC 134 and a high permeability co-blowing agent such as flourochloromethane, methyl chloride, ethyl chloride, chlorodifluoromethane, and 1,1-difluoroethane. The Canadian patent avoids the above problem when it employs significantly lower levels of HFC 134. The disclosed co-blowing agents are very soluble in alkenyl aromatic polymers and negatively impact foam

dimensional stability when employed with HFC 134 in blowing agent compositions comprising about 70 weight percent or more of HFC 134.

Japan Published Application 5-287111 relates extruded polystyrene foams made with a blowing agent of HFC 134 and 2-chloro-1,1,1,2-tetrafluoroethane (HCFC 124) in an 80/20 ratio by weight. Although the dimensional stability of the disclosed foams is not described, use of such blowing agents would result in dimensionally unstable foams due to the high solubility of HCFC 124 in polystyrene and its slow permeation rate through polystyrene foams.

U.S. Patent No. 5,182,040 relates azeotropic and near-azeotropic compositions described as useful as blowing agents in polymer foams among other uses. The compositions comprise HFC 134 and a co-blowing agent selected from among 1,1-difluoroethene (HFC 152a); 1-chloro-1,1-difluoroethane (HCFC 142b); dimethyl ether (DME); 1,1,1,2,3,3,3-heptafluoropropane (HFC 227ea); perfluorocyclobutane (HFC 318); n-butane; or isobutane. A specific foam embodiment of a polystyrene foam blown with a composition of 60-99 weight percent HFC 134 and 1-40 weight percent DME of certain physical properties (claim 1). Although the dimensional stability of any possible foams is not described, use of such co-blowing agents with about 70 weight percent or more HFC 134 would result in dimensionally unstable foams due to their high solubility in polystyrene and, in the case of some of the co-blowing agents, their slow permeation rate through polystyrene foams. Further, DME is very flammable.

U.S. Patent No. 5,278,196 relates plastic foams blown with a composition of 1,1,1,2,3,3,3-heptafluoropropane (HFC 227ea) and HFC 134 (claim 7). The reference does not describe a dimensionally stable, low density, extruded polystyrene foam blown with a composition comprising about 70 weight percent or more of HFC 134.

It was found surprising that a dimensionally stable, low density, extruded alkenyl aromatic polymer foam of low density and thick cross-section could be produced with a blowing agent formulation comprising about 70 weight percent or more of HFC 134a.

#### Summary of the Invention

According to the present invention, there is an extruded, dimensionally stable, closed cell alkenyl aromatic polymer foam. The foam comprises an alkenyl aromatic polymer material greater than 50 percent by weight of alkenyl aromatic monomeric units. The foam

has a density of about 16 to about 64 kilograms per cubic meter. The foam has a thickness in cross-section of 15 millimeters or more. The foam has a blowing agent composition comprising a primary blowing agent of about 70 to about 95 weight percent 1,1,2,2-tetrafluoroethane and a secondary blowing agent comprising about 30 to about 5 weight percent based upon the total moles of the blowing agent composition. Useful secondary blowing agent may have a vapor pressure of about 100 psia or more at 25 degrees Celsius. Useful secondary blowing agents having such a vapor pressure level include 1,1,1,2-tetrafluoroethane, carbon dioxide, nitrogen, helium, and argon. A useful secondary blowing agent not having such a vapor pressure level is water. The foam exhibits excellent dimensional stability.

According to the present invention, there is a process for making foam described above. The process comprises a) heating a alkenyl aromatic polymer material comprising greater than 50 percent by weight alkenyl aromatic monomeric units to form a melt polymer material; b) incorporating into the melt polymer material at an elevated pressure the blowing agent composition described above; c) the foamable gel being cooled to an desired foaming temperature; and d) extruding the foamable gel through a die into a zone of reduced pressure to form the foam.

#### Detailed Description

The present invention addresses the dimensional stability problem associated with use of high levels of HFC 134 in blowing agents when making closed cell alkenyl aromatic polymer foams of low density and thick cross-section. A secondary blowing agent is selected which has a low solubility in alkenyl aromatic polymers, especially polystyrene. The secondary blowing agent does not significantly plasticize the polymer matrix and render the foam susceptible to excessive expansion or contraction (collapse). Some useful secondary blowing agents have the additional desirable feature of permeating rapidly out of the foam. Rapid permeation out of the foam promotes dimensional stability in that it balances the permeation of air into the foam. The Internal cell gas pressure within the foam is more likely to remain stable or relatively stable over the long service life of the insulating foam. Maintenance of a relatively stable internal cell gas pressure makes expansion or contraction of the foam less likely.

Most useful secondary blowing agents have a vapor pressure of about 100 psia or more at 25 degrees Celsius. Since solubility of a blowing agent in a substrate polymer is

difficult to measure precisely, vapor pressure was chosen as a physical property to characterize the blowing agent. Vapor pressure corresponds approximately to solubility since blowing agents which have high vapor pressures usually have low solubility in substrate polymers; conversely, blowing agents which have low vapor pressures usually have high solubility in substrate polymers. Useful secondary blowing agents will be employed at a level of at least about 5 weight percent based upon the total moles of the blowing agent composition. A useful secondary blowing agent which does not exhibit such a vapor pressure level is water.

Particularly useful secondary blowing agents include 1,1,1,2-tetrafluoroethane, carbon dioxide, nitrogen, helium, argon, water, and mixtures of the foregoing.

Particularly useful blowing agent combinations include HFC 134/HFC 134a and HFC 134/carbon dioxide.

The blowing agent composition may comprise other blowing agents useful in minor proportions as long as HFC 134 comprises at least about 70 weight percent and the secondary blowing agent comprises at least about 5 weight percent based upon the total moles of the blowing agent composition. Other blowing agents include physical blowing agents and chemical blowing agents. Useful physical blowing agents include aliphatic hydrocarbons having 1-9 carbon atoms, aliphatic alcohols having 1-3 carbon atoms, and fully and partially halogenated aliphatic hydrocarbons having 1-4 carbon atoms. Aliphatic hydrocarbons include methane, ethane, propane, n-butane, isobutane, n-pentane, isopentane, neopentane, and the like. Aliphatic alcohols include methanol, ethanol, n-propanol, and isopropanol. Fully and partially halogenated aliphatic hydrocarbons include fluorocarbons, chlorocarbons, and chlorofluorocarbons. Examples of fluorocarbons include methyl fluoride, perfluoromethane, ethyl fluoride, 1,1-difluoroethane (HFC-152a), 1,1,1-trifluoroethane (HFC-143a), 1,1,1,2-tetrafluoroethane (HFC-134a), pentafluoroethane, difluoromethane, perfluoroethane, 2,2-difluoropropane, 1,1,1-trifluoropropane, perfluoropropane, dichloropropane, difluoropropane, perfluorobutane, perfluorocyclobutane. Partially halogenated chlorocarbons and chlorofluorocarbons include methyl chloride, methylene chloride, ethyl chloride, 1,1,1-trichloroethane, 1,1-dichloro-1-fluoroethane (HCFC-141b), 1-chloro-1,1-difluoroethane (HCFC-142b), chlorodifluoromethane (HCFC-22), 1,1-dichloro-2,2,2-trifluoroethane (HCFC-123) and 1-chloro-1,2,2,2-tetrafluoroethane (HCFC-124). Fully halogenated chlorofluorocarbons include trichloromonofluoromethane (CFC-11), dichlorodifluoromethane (CFC-12), trichlorotrifluoroethane (CFC-113),

1,1,1-trifluoroethane, pentafluoroethane, dichlorotetrafluoroethane (CFC-114), chloroheptafluoropropane, and dichlorohexafluoropropane. Chemical blowing agents include azodicarbonamide, azodiisobutyro-nitrile, benzenesulfonhydrazide, 4,4'-oxybenzene sulfonyl-semicarbazide, p-toluene sulfonyl semi-carbazide, barium azodicarboxylate, N,N'-dimethyl-N,N'-dinitrosoterephthalamide, and trihydrazino triazine.

The amount of blowing agent incorporated into the polymer melt material to make a foam-forming polymer gel is from about 0.2 to about 5.0 gram-moles per kilogram of polymer, preferably from about 0.5 to about 3.0 gram-moles per kilogram of polymer, and most preferably from about 1.0 to 2.50 gram-moles per kilogram of polymer.

10 The present foam has a density of from about 16 to about 64 and most preferably from about 25 to about 48 kilograms per cubic meter according to ASTM D-1622-88. The foam has an average cell size of from about 0.1 to about 0.5 and preferably from about 0.2 to about 0.4 millimeters according to ASTM D3576-77.

15 The present foam is particularly suited to be formed into a plank, desirably one having a cross-sectional area of about 30 square centimeters or more and a minor dimension in cross-section (thickness) of about 15 millimeters or more.

The present foam is closed cell. Preferably, the present foam is greater than 90 percent closed-cell according to ASTM D2856-87.

20 The present foam has excellent dimensional stability. The foam exhibits dimensional change in any direction of about four (4) percent or less according to ASTM D2126/C578.

The present foam comprises an alkenyl aromatic polymer material. Suitable alkenyl aromatic polymer materials include alkenyl aromatic homopolymers and copolymers of alkenyl aromatic compounds and copolymerizable ethylenically unsaturated comonomers. The alkenyl aromatic polymer material may further include minor proportions of non-alkenyl aromatic polymers. The alkenyl aromatic polymer material may be comprised solely of one or more alkenyl aromatic homopolymers, one or more alkenyl aromatic copolymers, a blend of one or more of each of alkenyl aromatic homopolymers and copolymers, or blends of any of the foregoing with a non-alkenyl aromatic polymer. Regardless of composition, the alkenyl aromatic polymer material comprises greater than 50 and preferably about 70 weight percent or more alkenyl aromatic monomeric units. Most preferably, the alkenyl aromatic polymer material is comprised entirely of alkenyl aromatic monomeric units.

25  
30

Suitable alkenyl aromatic polymers include those derived from alkenyl aromatic compounds such as styrene, alphanethylstyrene, ethylstyrene, vinyl benzene, vinyl toluene, chlorostyrene, and bromostyrene. A preferred alkenyl aromatic polymer is polystyrene. Minor amounts of monoethylenically unsaturated compounds such as C2-6 alkyl acids and esters, ionomeric derivatives, and C4-6 dienes may be copolymerized with alkenyl aromatic compounds. Examples of copolymerizable compounds include acrylic acid, methacrylic acid, ethacrylic acid, maleic acid, itaconic acid, acrylonitrile, maleic anhydride, methyl acrylate, ethyl acrylate, isobutyl acrylate, n-butyl acrylate, methyl methacrylate, vinyl acetate and butadiene. Preferred structures comprise substantially (i.e., greater than 90 percent by weight and more preferably greater than 95 percent by weight) and most preferably entirely of polystyrene.

The present alkenyl aromatic polymer foam is generally prepared by heating an alkenyl aromatic polymer material to form a plasticized or melt polymer material, incorporating therein a blowing agent to form a foamable gel, and extruding the gel through a die to form the foam product. Prior to mixing with the blowing agent, the polymer material is heated to a temperature at or above its glass transition temperature or melting point. The blowing agent may be incorporated or mixed into the melt polymer material by any means known in the art such as with an extruder, mixer, blender, or the like. The blowing agent is mixed with the melt polymer material at an elevated pressure sufficient to prevent substantial expansion of the melt polymer material and to generally disperse the blowing agent homogeneously therein. Optionally, a nucleator may be blended in the polymer melt or dry blended with the polymer material prior to plasticizing or melting. The foamable gel is typically cooled to a lower temperature to optimize physical characteristics of the foam structure. The gel may be cooled in the extruder or other mixing device or in separate coolers. The gel is then extruded or conveyed through a die of desired shape to a zone of reduced or lower pressure to form the foam structure. The zone of lower pressure is at a pressure lower than that in which the foamable gel is maintained prior to extrusion through the die. The lower pressure may be superatmospheric or subatmospheric (vacuum), but is preferably at an atmospheric level.

In addition, a nucleating agent may be added in order to control the size of foam cells. Preferred nucleating agents include inorganic substances such as calcium carbonate, talc, clay, titanium dioxide, silica, barium stearate, diatomaceous earth, mixtures of citric acid and sodium bicarbonate, and the like. The amount of nucleating agent employed may range



from about 0.01 to about 5 parts by weight per hundred parts by weight of a polymer resin. The preferred range is from 0.1 to about 3 parts by weight.

5 Various additives may be incorporated in the present foam structure such as inorganic fillers, pigments, antioxidants, acid scavengers, ultraviolet absorbers, flame retardants, processing aids, extrusion aids, and the like.

An infrared attenuating agent such as carbon black, titanium dioxide, or graphite may be added to the polymer melt or foamable gel during manufacture to yield an end product foam of low thermal conductivity. Loadings typically vary from about 2 to about 10 percent by weight based upon the weight of the alkenyl aromatic polymer material.

10 While embodiments of the foam composition and the process of the present invention have been shown with regard to specific details, it will be appreciated that depending upon the manufacturing process and the manufacturer's desires, the present invention may be modified by various changes while still being fairly within the scope of the novel teachings and principles herein set forth.

WHAT IS CLAIMED IS:

1. An extruded, dimensionally stable, closed cell alkenyl aromatic polymer foam, comprising: an alkenyl aromatic polymer material comprising greater than 50 percent by weight of alkenyl aromatic monomeric units, the foam having a density of about 16 to about 64 kilograms per cubic meter, the foam having a thickness in cross-section of 15 millimeters or more, the foam having a blowing agent composition comprising a primary blowing agent of about 70 to about 95 weight percent 1,1,2,2-tetrafluoroethane and a secondary blowing agent comprising about 30 to about 5 weight percent based upon the total moles of the blowing agent composition, the secondary blowing agent being selected from the group consisting essentially of 1,1,1,2-tetrafluoroethane, carbon dioxide, nitrogen, argon, and water.
2. The foam of Claim 1, wherein the secondary blowing agent is 1,1,1,2-tetrafluoroethane.
3. The foam of Claim 1, wherein the secondary blowing agent is carbon dioxide.
4. The foam of Claim 1, wherein the secondary blowing agent is nitrogen.
5. The foam of Claim 1, wherein the secondary blowing agent is argon.
6. The foam of Claim 1, wherein the secondary blowing agent is water.
7. The foam of Claim 1, wherein the secondary blowing agent is has a vapor pressure of 100 psia or more at 25 degrees Celsius.
8. A process for making an extruded, dimensionally stable, closed cell alkenyl aromatic polymer foam structure, the foam having a density of about 16 to about 64 kilograms per cubic meter, the foam having a thickness in cross-section of 15 millimeters or more, comprising:
  - a) heating a alkenyl aromatic polymer material comprising 50 percent or more by weight alkenyl aromatic monomeric units to form a melt polymer material;
  - b) incorporating into the melt polymer material at an elevated pressure a blowing agent composition comprising a primary blowing agent of about 70 to about 95 weight percent 1,1,2,2-tetrafluoroethane and a secondary blowing agent being selected from the group consisting essentially of 1,1,1,2-tetrafluoroethane, carbon dioxide, nitrogen, argon, and water;

c) the foamable gel being cooled to a desired foaming temperature; and  
d) extruding the foamable gel through a die into a zone of reduced pressure to form the foam.

5 9. The process of Claim 8, wherein the secondary blowing agent is 1,1,1,2-tetrafluoroethane.

10. The process of Claim 8, wherein the secondary blowing agent is carbon dioxide.

11. The process of Claim 8, wherein the secondary blowing agent is nitrogen.

12. The process of Claim 8, wherein the secondary blowing agent is argon.

13. The process of Claim 8, wherein the secondary blowing agent is water.

10 14. The process of Claim 8, wherein the secondary blowing agent is has a vapor pressure of 100 psia or more at 25 degrees Celsius.

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/26322

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08J9/14 C08J9/12

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P	WO 98 03581 A (DU PONT ;YORK ROBERT O (US); HAMMEL HOWARD S (US); CREAZZO JOSEPH) 29 January 1998 see claims 1,4	1,2
A	EP 0 445 847 A (DOW CHEMICAL CO) 11 September 1991 see page 4, line 48 - page 5, line 7 see claims	1-14



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&amp;" document member of the same patent family

Date of the actual completion of the international search

20 April 1999

Date of mailing of the international search report

28/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Oudot, R

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 98/26322

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9803581 A	29-01-1998	AU 3964097 A	10-02-1998
EP 0445847 A	11-09-1991	AU 1712088 A	04-11-1988
		CA 1309221 A	27-10-1992
		DE 3867700 A	27-02-1992
		EP 0291179 A	17-11-1988
		FI 94871 B	31-07-1995
		GR 3004026 T	31-03-1993
		JP 10292077 A	04-11-1998
		JP 9104780 A	22-04-1997
		JP 2503657 T	01-11-1990
		JP 2624813 B	25-06-1997
		KR 9514239 B	23-11-1995
		WO 8808013 A	20-10-1988

